



Polypropylene Borsoft™ SD233CF

Description

Borsoft SD233CF is a very soft random heterophasic copolymer.

This grade is suitable for use on chill roll processes.

Applications

Borsoft SD233CF is recommended for

Stationery folders	Hygienic film
Food packaging	Coating of textile fibres
Textile packaging film	Coextrusion applications
Technical and protection film	Property modification in other application fields
Substitution of other plastics	(engineering, compounding, fibre, injection moulding)

Special features

Borsoft SD233CF is optimised to deliver:

Very high softness	Excellent heat seal properties
Outstanding mechanical properties	Easy processing on standard cast film lines
Very good optical properties	Good radiation resistance (for sterilisation)

Physical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Density	900 - 910 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	7 g/10min	ISO 1133
Flexural Modulus ¹	400 MPa	ISO 178
Melting temperature (DSC)	138 - 142 °C	ISO 3146
Vicat softening temperature A50, (10 N) ¹	107 °C	ISO 306

¹ Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

Film Properties

Specific film values evaluated on chill roll films, produced with Borealis internal standard conditions with a thickness of 50 µm. When compared to films which were produced under other conditions. It should be taken into account that the film properties are strongly dependent on the processing conditions.

Property	Typical Value	Test Method
	Data should not be used for specification work	
Instrumented puncture test	Total Penetration Energy	35 J
	Force	1200 N
Haze		< 4 %
Gloss at 20 degree (of arc)		> 90 %
Tensile Strain at Break	MD	650 - 850 %
		ISO 7765-2
		ASTM D 1003
		ASTM D 2457
		ISO 527-3

Borsoft is a trademark of Borealis A/S, Denmark.

Borealis AG | Wagramerstrasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



Polypropylene

Borsoft SD233CF

Tensile Strength	/TD		
Tensile Strength	MD	30 - 50 MPa	ISO 527-3
Tensile Modulus	TD	25 - 45 MPa	ISO 527-3
	MD	150 - 250 MPa	ISO 527-3
	/TD		

Storage

Borsoft SD233CF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our Safety Data Sheet for this product.

Safety

The product is not classified as a dangerous preparation. Please see our Safety Data Sheet for details on various aspects of safety, recovery and disposal of the product, for more information contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our Safety Data Sheet for details on various aspects of safety, recovery and disposal of the product, for more information contact your Borealis representative.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Data Sheet
 Statement on chemicals, regulations and standards
 Statement on compliance to food contact regulations
 Statement on compliance to regulations on medical use



Polypropylene
Borsoft SD233CF

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.