



Technical Data Sheet

Clearflex® CM406

Linear Low Density Polyethylene

DESCRIPTION

Clearflex® CM406 is a hexene copolymer linear low density polyethylene (C6-LLDPE), additivated with antioxidants, suitable for cast film extrusion.

Films manufactured with Clearflex® CM406 are characterised by high clarity, optimum elongation, optimum impact and tear resistance.

APPLICATIONS

Clearflex® CM406 is recommended for the production of low cling cast film with optimum optical properties and good mechanical resistance.

TYPICAL

PROPERTIES

Properties	Test Method	Typical value	
Resin Properties			
Melt Flow Index _{190 °C / 2.16 kg} (g/10')	ASTM D1238	3.6	
Density (g/cm ³)	ASTM D1505	0,926	
Melting point (°C)	PE Method	127	
Brittleness point (°C)	ASTM D746	<-70	
Vicat softening point _{1 kg} (°C)	ASTM D1525	103	
Film Properties¹ - Thickness 23 µm			
Tensile strength at yield (MPa)	MD	ISO 527-3	11
	TD		11
Tensile strength at break (MPa)	MD	ISO 527-3	36
	TD		30
Elongation at break (%)	MD	ISO 527-3	730
	TD		850
1% Secant Modulus (MPa)	MD	ISO 527-3	240
	TD		250
Tear resistance (Elmendorf) (N/mm)	MD	ISO 6383-2	80
	TD		180
Coefficient of Friction (dynamic)		ISO 7765-1	> 0.5
Impact resistance, F ₅₀ (g) (Dart Drop Test)		ISO 8295	90
Haze (%)		ISO 14782	4
Gloss, 45° (%)		ASTM D 2457	85

¹ Typical value for a cast film extruded at 220°-270°C. Actual properties are typical and may vary depending upon operating conditions and additive package.

EXTRUSION CONDITIONS

Clearflex® CM406 is easily processable using cast film technology. Melt temperature should be between 220°C and 270°C.
Clearflex® CM406 can be extruded at thickness below 25µm.

STORAGE AND HANDLING

Clearflex CM406 is supplied in pellet form. This material may readily be conveyed and bulk-fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping be practised throughout your facility.

Before using this product, read and understand the current POLIMERI EUROPA Safety Data Sheet for this product.

AVAILABILITY

Contact the POLIMERI EUROPA sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Clearflex® CM406 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications.
Certificates of compliance are available upon request.

TECHNICAL SERVICE

POLIMERI EUROPA SpA
Piazza Boldrini 1
20097 S. Donato Milanese (Milan)-Italy
Tel. +39 02 520.1
Fax +39 02 520.42436

POLIMERI EUROPA SAS
Route des Dunes BP59
F-59279 MARDYCK
France
Tel. (33) 3 28235514
Fax (33) 3 28235520

HEADQUARTERS

POLIMERI EUROPA SpA
Piazza Boldrini 1
20097 San Donato Milanese (Milan)-Italy
Tel. +39 02 520.1
Fax +39 02 520.42901
info.polyethylene@polimerieuropa.com
www.polimerieuropa.com

IMPORTANT: The descriptions and figures contained herein are provided to customer by way of a general information for the purposes the product is intended for. These reflect POLIMERI EUROPA's knowledge at the time of publication. Since the acknowledged various product applications by customers cannot be controlled by POLIMERI EUROPA, in no circumstances may POLIMERI EUROPA be held responsible for the results obtained from the customers manufacturing processes or for the product used in combination with other substances. By the information contained herein POLIMERI EUROPA won't release any warranty and/or any legal responsibility and/or give any suggestion on the use of the product, or grant any franchise on existing patents. The end-user, transformer shall always check the specific suitability of the product for the purposes it is intended for and its compatibility with process specifications. Moreover, the buyer shall check that retention, use or marketing of our products be in compliance with health, environmental as well as work-and-consumer-related safety requirements. It is the buyer's responsibility to inform end-user. In no circumstances will POLIMERI EUROPA be held responsible should not the buyer meet the obligations and recommendations indicated herein