



DOW™ LDPE PG 7008 (Extrusion Coating) Low Density Polyethylene Resin

Overview

Dow LDPE PG 7008 Polyethylene Resin is typically used in extrusion coating applications. Dow LDPE PG 7008 Polyethylene Resin can be readily processed using conventional LDPE extrusion coating hardware of melt temperatures of 270 to 335°C, preferably less than 290°C, for best sensory performance. Dow LDPE PG 7008 Polyethylene Resin provides low volatile organic carbon (VOC) emissions in extrusion, contributing to low factory emissions and optimal sensory performance. When processed on suitable hardware, Dow LDPE PG 7008 Polyethylene Resin exhibits excellent draw down good edge stability and low neck-in.

Applications:

- Paper, board and foil coatings for packaging, food and non-food

Complies with:

- U.S. FDA 21 CFR 177.1520(c)2.2
- EU, No 10/2011
- Canadian HPFB No Objection

Consult the regulations for complete details.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.918 g/cm ³	0.918 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	7.7 g/10 min	7.7 g/10 min	ISO 1133
Molding Shrinkage - Flow (428°F (220°C))	0.026 in/in	2.6 %	ASTM D955 ¹
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus - 2% Secant	23200 psi	160 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	1160 psi	8.00 MPa	
Break	1450 psi	10.0 MPa	
Tensile Elongation (Break)	450 %	450 %	ASTM D638
Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Seal Initiation Temperature	221 °F	105 °C	Dow Method ²
Water Vapor Transmission	17 g/100 in ² /24 hr	270 g/m ² /24 hr	ASTM E398-83 ³
Minimum Heat Seal Temperature	212 to 248 °F	100 to 120 °C	Dow Method
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	192 °F	89.0 °C	ISO 306/A
Melting Temperature	223 °F	106 °C	DSC
Extrusion	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Temperature	518 to 635 °F	270 to 335 °C	
Minimum Coating Weight	3.1 lb/ream	5.0 g/m ²	Dow Method ⁴
Neck-in	2.6 in	65.0 mm	Dow Method ⁵

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ 0.5 seconds injection.

² Temperature required to reach 3 N/15 mm for a 25 g/m² coating of PG 7008 onto paper

³ 38°C, 90% RH
Divide by coating weight in g/m² to obtain actual WVTR.

⁴ 290°C set temperature.

⁵ 100 m/min, 25 g/m² coatings at 290°C set temperature.

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

Additional Information

North America		Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+31-11567-2626
	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369		
Latin America		South Africa	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

www.dowplastics.com

This document is intended for use within Asia Pacific, Europe

Published: 2009-06-02

© 2012 The Dow Chemical Company

