

ExxonMobil™ LDPE LD 650

Low Density Polyethylene Resin

Product Description

LD650 is an easy flowing LDPE grade with a good flexibility and excellent toughness.

General

Availability ¹	• Africa & Middle East	• Asia Pacific	• Europe
Additive	• Antiblock: No	• Slip: No	• Thermal Stabilizer: No
Applications	• Caps • Closures • Compounding	• Food Packaging Containers • Houseware Articles • Injection Molding	• Masterbatch Base Resin • Toys • Viscosity Modifier
Revision Date	• March 2010		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.914 g/cm ³	0.914 g/cm ³	ExxonMobil Method
Melt Index ²	22 g/10 min	22 g/10 min	ExxonMobil Method
Peak Melting Temperature	217 °F	103 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	178 °F	81.0 °C	ISO 306

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Modulus	17400 psi	120 MPa	ISO 527-2/1A/1
Tensile Stress at Break	1160 psi	8.00 MPa	ISO 527-2/1A/50
Tensile Strain at Break	120 %	120 %	ISO 527-2/1A/50
Shore Hardness (Shore D)	40	40	ISO 868

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

The molded properties have been measured on 4 mm (157.5 mil) thick injection molded specimen, based on ISO 1872-2.

Notes

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Value reported is an estimate based on ExxonMobil's correlation from melt flow rate data measured at other standard conditions, based on ASTM D 1238.

Typical properties: these are not to be construed as specifications.

© 2010 Exxon Mobil Corporation. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Chemical Emblem, the "Interlocking X" Device, Enable, Exceed, Exact, Exxco, Escorene, Escor, Iotek, NTX, Polybilt, Paxon and Optema are trademarks or service marks of Exxon Mobil Corporation.