

ExxonMobil LLDPE

LL 6201 SERIES

Wire & Cable Applications Resins

Description

LL 6201XR/RQ is a C4 Ziegler Natta LLDPE recommended for compounding applications.

Additive Package	Antiblock	Slip	Thermal Stabilizer	Physical Appearance
LL 6201XR	No	No	Yes	Pellets
LL 6201RQ	No	No	Very Low	Coarse Powder

Resin Properties	Test Based On	Typical Value / Unit	
Melt Index	ASTM D1238	50 g/10 min	
Density	ASTM D4703 / D1505	0.926 g/cm ³	
Peak Melting Temperature	ASTM D3418	123 °C	253 °F
Crystallization Point	ASTM D3418	105 °C	221 °F

Revised 12/03