

LDPE	LLDPE	MDPE	HDPE	PP	PVC	GPPS	HIPS	EPS	PET	ABS	SBR	PBR	PC	E.P.
------	-------	------	------	----	-----	------	------	-----	-----	-----	-----	-----	----	------



HD –MF3713

1) Product Description:

MF3713 is a high molecular weight high density polyethylene.

2) Applications:

- Bags, Products for Use in Property Modification

3) Typical data.

Properties	Value	Unit	Test method
Density	0.937	g/cm ³	ISO 1183
MFR (190°C/21.6kg)	13	dg/min	ISO 1133
MFR (190°C/2.16kg)	0.1	dg/min	ISO 1133
Tensile Modulus	735	MPa	ISO527-1
Tensile Strength(MD)	46	MPa	ISO 527-1,3
Tensile Strength(TD)	46	MPa	ISO 527-1,3
Tensile Strain at Break(MD)	550	%	ISO 527-1
Tensile Strain at Break(TD)	650	%	ISO 527-1
Elemendorf tear strength(MD)	210	mN	ISO 6383-2
Elemendorf tear strength(TD)	1100	mN	ISO 6383-2
Vicat Temp,(A50,50°C/h,10N)	121	°C	ISO 306

The above data are typical laboratory average . They are intended to serve as guides only

Producer: Arya Sasol Petrochemical Co.

Licensor: Basell

Packing: Supplied in pellet form and can be packed in 25 kg Bags, 1 ton semi bulk or 17 ton bulk