



GPPS

Technical Datasheet



Parameter	Measured	Environmental Conditions
Density/Bulk Density	1.04 gr/cm³	ASTM D895
Flexural Modulus	2911 mpa	ASTM 790
Tensile Strength	50 mpa	ASTM D638
Vicat Softening	105'c	ASTM D1525
Heat Distortion Temperature (HDT)	97'c	ASTM D648
MFI	11	ASTM D1238
Grades	MP08	---
Determination of Residual Styrene Monomer	<500	44