

IDZOOOS			Melt Index	413
LD/000S			Density	0.941
Material Properties				
Resin Properties	ASTM Test	Unit	Typical Value	
Density	D 1505	g/cm³	0.941	
Melt Index (190°C/2.16kg)	D 1238	g/10 min	413	
Vinyl Acetate Content	Manufacturer Method	wt %	27	
Peak Melting Temperature	Manufacturer Method	°F (°C)	145° (63°)	
Thermal				
Vicat Softening Temperature	D 1525	°F (°C)	144° (62°)	

Osterlene LD7000S is a high vinyl acetate copolymer resin designed for applications requiring outstanding sealability.

□ LD7000S is a high flow VA coploymer compatible with natural tackifiers and most waxes.

Legal statement - Contact your Osterman Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

*Typical Properties: these are not to be construed as specifications.



The information on this document is, to our knowledge, true, and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Osterman products and any written or oral information, suggestions or technical advice from Osterman are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Osterman materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Osterman makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

Osterman & Company, Inc. - 726 South Main Street, Cheshire, CT 06410 T (203) 272-2233 • Customer Service (800) 914-4437