

## REPSOL EBANTIX<sup>®</sup> E1704

EBA REPSOL EBANTIX<sup>®</sup> E1704 is a copolymer suitable for blown film applications where good processability, flexibility and good mechanical properties are required. The butyl acrylate content is 17%. It contains antioxidant additives.

### Applications

- Film extrusion.
- Stretch hood film.

Recommended melt temperature 180°C. Processing characteristics of E1704 are similar to LDPE and conventional polyethylene extruders are recommended. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
<b>GENERAL</b>			
Melt flow rate (190°C, 2.16kg)	0.4	g/10 min	ISO 1133
Butyl acrylate content	17	%	Internal
Density at 23°C	925	kg/m <sup>3</sup>	ISO 1183
Melting Point	96	°C	Internal
<b>FILM<sup>(1)</sup></b>			
Dart drop (F <sub>50</sub> )	1400	g	ISO 7765-1
Tear resistance (Elmendorf) (MD/TD)	360/390	cN	ISO 6383-2
Tensile strength at break (MD/TD)	29/30	MPa	ISO 527-3
Elongation at break (MD/TD)	750/850	%	ISO 527-3

(1) 100 µm thickness film, blow up ratio 1:2.5, frost line height 50 cm.

### Storage

EBA REPSOL EBANTIX<sup>®</sup> E1704 should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 50°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and the properties of the transformed product.



[1/2]

### Disclaimer

This grade complies with the European regulations for materials for use in food contact. This grade is not intended to be used in medical, pharmaceutical, or healthcare applications, therefore Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

### Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet
- Statement on compliance with food contact regulations

**Recommended consumption period:** 12 months from the raw material reception

July 2021



[2/2]