

# SABIC® LLDPE 318BJ

## LINEAR LOW DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® LLDPE 318BJ is a butene linear low density polyethylene resin typically designed for easy processing and specially formulated for optimum thermal stability at high temperatures used in cast film extrusion. Cast film produced from SABIC® LLDPE 318BJ exhibit excellent optical properties, puncture resistance and tear strength .SABIC® LLDPE 318BJ is TNPP free. This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL APPLICATIONS

SABIC® LLDPE 318BJ resin is typically used for hand and pallet stretch wrap, cling film, melt embossed film and other genera-purpose application.

### TYPICAL PROPERTY VALUES

Revision 20180125

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 190 °C and 2.16 kg	2.8	dg/min	ASTM D1238
<b>Density</b>	918	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
stress at break	13	MPa	ASTM D638
strain at yield	16	%	ASTM D638
stress at yield	12	MPa	ASTM D638
strain at break	710	%	ASTM D638
<b>Flexural test</b>			
Secant modulus at 1% elongation	251	MPa	ASTM D790
<b>Hardness Shore D <sup>(1)</sup></b>	48	-	ISO 868
<b>OPTICAL PROPERTIES</b>			
<b>Gloss (45°)</b>	91	% <sub>o</sub>	ASTM D2457
<b>Haze <sup>(2)</sup></b>	2.1	%	ASTM D1003
<b>FILM PROPERTIES</b>			
<b>Dart impact</b>	2.6	kJ/m	ISO 7765-2
<b>Tear strength TD</b>	140	kN/m	ISO 6383-2
<b>Protrusion Puncture resistance</b>	2.0	J	ASTM D5748-95
<b>Elastic recovery &amp; Stress retention</b>			
Elastic recovery	51.9	%	ASTM D5459-95

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Stress retention	78.1	%	ASTM D5459-95
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
at 10 N (VST/A)	102	°C	ISO 306
<b>DSC test</b>			
melting point	121	°C	SABIC method
<b>ELECTRICAL PROPERTIES</b>			
<b>Volume resistivity</b>	8.5E15	Ohm.cm	ASTM D257
<b>Dissipation factor at 60 Hz</b>	5.0E-4	-	ASTM D150
<b>Dielectric constant at 60 Hz</b>	2.2	-	ASTM D150
<b>Dielectric strength at 2000 V/sec</b>	>30	V/μm	ASTM D149

(1)

Properties are determined on 20 μm cast stretch film produced on a 2 m commercial cast stretch line: melt temperature 270 °C, chill roll temperature 20 °C and line speed of 450 m/min

(2) Properties have been measured by producing 30 μm film with 2.5 BUR using 100% 318BJ.

## PROCESSING CONDITIONS

SABIC® LLPDE 318BJ is extrudable with conventional cast film extrusion equipment. Minor machine modifications may be required for optimum use.

Cast film melt temperature: 250 - 300°C Chill roll temperature: 20°C

## HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

318BJ resin is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical/medical applications.

## QUALITY

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO 9001.

## ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC Europe considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC Europe whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.



## STORAGE AND HANDLING

Polyethylene resins should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions, which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process Polyethylene resins within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.