

SABIC[®] LLDPE 318CNJ

LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

318CNJ is a Linear Low Density Polyethylene TNPP free grade designed for wire and cable applications. It contains optimized level of antioxidants and does not contain any slip and antiblock additives. Sufficient antioxidant and Cu-inhibitor should be added to meet specific ageing requirements. For jacketing applications, addition of Carbon Black or UV stabilizer is required.

TYPICAL APPLICATIONS

One-step or two-step Silane cross-linkable insulation for Low Voltage power insulation cable, Aerial bundle cable and suitable for telecommunication and Low Voltage power cable jacketing.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190°C and 2.16 kg	2.8	g/10 min	ASTM D1238
Density	918	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Hardness (Shore D) ⁽¹⁾	51	-	ASTM D2240
FILM PROPERTIES			
Tensile Properties			
stress at yield	10	MPa	ASTM D638
stress at break	18	MPa	ASTM D638
strain at yield	17	%	ASTM D638
strain at break	555	%	ASTM D638
1% secant modulus	174	MPa	ASTM D638
THERMAL PROPERTIES			
Peak Melting Temperature	120	°C	SABIC method
ELECTRICAL PROPERTIES			
Volume Resistivity			
at 500V	6.8x10 ¹⁷	Ωcm	ASTM D257
Dielectric Constant			
at 1 kHz	2.25	-	ASTM D150
Dissipation Factor			
at 1 kHz	7.0x10 ⁻⁴	-	ASTM D150
Dielectric Strength			
at 1000 V/sec	37	kV/mm	ASTM D149

(1) Based on Injection molded specimens.



HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet (www.SABIC.com). Additional specific information can be requested via your local Sales Office.”

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical/medical applications.

STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions, which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.