

SABIC® COHERE™ 8402

METALLOCENE POLYOLEFIN PLASTOMER

DESCRIPTION

SABIC® COHERE™ 8402 grade is an ethylene-octene copolymer produced via solution polymerization using metallocene catalyst. It performs well high performance LLDPE cast film and deliver outstanding toughness optics. SABIC® COHERE™ 8402 provides excellent performance as cling layer in stretch wrap film.

TYPICAL APPLICATIONS

Low temperature sealing layer for high value packaging (low SIT, seal through contamination, toughness improvement) and cast stretch film.

TYPICAL PROPERTY VALUES

Revision 20180112

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190°C and 2.16 kg	3.5	g/10 min	ASTM D1238
Density	902	kg/m ³	ASTM D1505
Mooney viscosity (ML 1+4, 121 °C)	10	MU	ASTM D1646
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile Strength at Break ⁽²⁾	200	kgf/cm ²	ASTM D638
Tensile Elongation at Break ⁽²⁾	850	%	ASTM D638
Flexural Modulus (1% Secant)	760	kgf/cm ²	ASTM D790
Tear Strength (Type C)	85	kgf/cm ²	ASTM D624
Hardness			
Shore A (1 sec)	89	-	ASTM D2240
Shore D (1 sec)	40	-	ASTM D2240
OPTICAL PROPERTIES			
Haze	0.5	%	ASTM D1003
FILM PROPERTIES			
Tensile test film ⁽³⁾			
stress at break, MD	50	MPa	ASTM D882
stress at break, TD	44	MPa	ASTM D882
elongation at break, MD	520	%	ASTM D882
elongation at break, TD	600	%	ASTM D882
1% secant modulus, MD	64	MPa	ASTM D882
1% secant modulus, MD	78	MPa	ASTM D882

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dart Impact F50 ⁽³⁾	>1000	g	ASTM D1709
Elmendorf Tear Strength ⁽³⁾			
MD	12	g/μm	ASTM D1922
TD	17	g/μm	ASTM D1922
THERMAL PROPERTIES			
Melting Point	~100	°C	SABIC method
Glass Transition Temperature, T _g	-32	°C	SABIC method

(1) Evaluated using compression molded sample.

(2) Crosshead speed: 500mm/min.

(3) Properties have been measured by producing 40 μm film cast line using 100% COHERE™ 8402.

PROCESSING CONDITIONS

Typical processing conditions for COHERE™ 8402 are:

Barrel temperature: 250 - 300°C

Chill roll temperature: 15 - 25 °C

FOOD REGULATION

Please contact the local Sales / Technical representative for details.

DISCLAIMER

The grades are not intended for and must not be used in any pharmaceutical / medical applications.

STORAGE AND HANDLING

The resin should be stored in a manner to prevent a direct exposure to sunlight and / or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC® would not give warranty to bad storage conditions that may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.