

Description

Polypropylene PPH 3061 is homopolymer with a Melt Flow Index of 1.9 g/10 min.

Polypropylene PPH 3061 is intended for the production of blow moulded containers, sheets, high tenacity tapes and twines, tapes for woven sack manufacture and sheet for thermoforming.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	1.9
Mechanical properties			
Tensile Strength at Yield	ISO 527-2	MPa	33
Elongation at Yield	ISO 527-2	%	10
Tensile modulus	ISO 527-2	MPa	1400
Flexural modulus	ISO 178	MPa	1300
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m ²	6
Charpy Impact Strength (notched) at 23°C	ISO 179	kJ/m ²	7
Hardness Rockwell - R-scale	ISO 2039-2		90
Thermal properties			
Melting Point	ISO 3146	°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			85
10N-50°C per hour			150
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			55
0.45 MPa - 120°C per hour			100
Other physical properties			
Density	ISO 1183	g/cm ³	0.905
Bulk Density	ISO 1183	g/cm ³	0.525

Safety and Product Stewardship

For safe use and handling, please refer to the Safety Data Sheet.

A Product Stewardship certificate giving the conformity to various regulations or statements on absence of certain chemicals is also available on our web site www.polypropylene.totalpetrochemicals.com

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within Total Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.