

CAMPUS® Datasheet



Novamid® 2030CA FC - PA666
DSM Engineering Plastics

Product Texts


High Viscosity, Film Extrusion, Lubricated, Food Contact Quality, Nucleated

ISO 1043 PA6/66


| Rheological properties | dry / cond | Unit | Test Standard |
|-------------------------------|------------|------------------------|---------------------|
| Melt volume-flow rate, MVR | 2.3 / * | cm ³ /10min | ISO 1133 |
| Temperature | 230 / * | °C | ISO 1133 |
| Load | 2.16 / * | kg | ISO 1133 |
| Thermal properties | dry / cond | Unit | Test Standard |
| Melting temperature, 10°C/min | 200 / * | °C | ISO 11357-1/-3 |
| Other properties | dry / cond | Unit | Test Standard |
| Humidity absorption | 2.8 / * | % | Sim. to ISO 62 |
| Density | 1130 / - | kg/m ³ | ISO 1183 |
| Material specific properties | dry / cond | Unit | Test Standard |
| Viscosity number | 246 / * | cm ³ /g | ISO 307, 1157, 1628 |

Diagrams

Viscosity-shear rate



Shearstress-shear rate



Characteristics

Processing

Film Extrusion, Other Extrusion

Additives

Lubricants

Delivery form

Pellets

Regional Availability

Asia Pacific

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Novamid® 2030CA FC - PA666
DSM Engineering Plastics

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2018. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.