



IDEMITSU PS HT50

PRODUCT INFORMATION

High Impact PS

FEATURES	APPLICATIONS
<ul style="list-style-type: none">• High Impact	<ul style="list-style-type: none">• Audio/TV/VTR Housing• Household Items

PROPERTY	TESTING METHOD	UNITS	VALUES
Specific Gravity	ASTM D 792	-	1.04
Melt Flow Rate (200/5)	ASTM D 1238	g/10 min	4.0
Tensile Strength (Break)	ASTM D 638	kg/cm ²	310
Ultimate Elongation	ASTM D 638	%	40
Flexural Strength	ASTM D 790	kg/cm ²	560
Flexural Modulus	ASTM D 790	kg/cm ²	22,000
Izod Impact Strength	ASTM D 256	kg.cm/cm	8.5
Heat Distortion Temperature	ASTM D 648	°C	85
Vicat Softening Point	ASTM D 1525	°C	107
Glossiness	ASTM D 523	%	50
Linear Mold Shrinkage	ASTM D 955	cm/cm	0.004 ~ 0.007
Rockwell Hardness	ASTM D 785	L scale	L60
Dupont Impact Strength	ASTM D3029	kg.cm	100
Coefficient of Linear Thermal Expansion	ASTM D696	* 10 ⁻⁵ mm/mm / °C	5 ~ 10
Water Absorption	ASTM D570	%	< 0.1
Flammability	UL 94	Flame Class	HB
Hot Wire Ignition (HWI)	UL 746A	HWI PLC	4
High Arc Ignition (HAI)	UL 746A	HAI PLC	0
Electrical RTI	UL 746B	°C	50
Mechanical Impact RTI	UL 746B	°C	50
Mechanical Strength RTI	UL 746B	°C	50

Notes:

- The properties of resin summarized in this brochure are typical, or average properties measured intended as guides only, not as specification limits.
- All values of UL testing methods refer to minimum thickness of 1.5mm. Please contact Petrochemicals (M) Sdn. Bhd. for values of other thickness.
- Abbreviations:
PLC = Performance Level Categories
RTI = Relative Temperature Index

CERTIFICATIONS	FOOD CONTACT
<ul style="list-style-type: none">• UL (File No.:E63304)• JET (DENTORI)• ISO9001:2008 (Quality Management System)	Please contact Petrochemicals (M) Sdn. Bhd. for further information on the certification/compliance/suitability of the product for food contact application.

All information is furnished in good faith, without warranty, representation, inducement or a license of any kind. No guarantee is given that IDEMITSU PS's product will be suitable in purchasers' formulations or processes for any particular end use.



PETROCHEMICALS (M) SDN. BHD.
PLO 408, Off Jalan Pekeliling,
Pasir Gudang Industrial Estate,
81700 Pasir Gudang, Johor, Malaysia.
Tel: +607-2596300, Fax: +607-2596320