

Processing/Physical Characteristics	Value	Unit
<b>ISO Data</b>		
Melt flow index, MFI	20	g/10min
Temperature	230	°C
Load	2.16	kg
<b>Mechanical properties</b>		
<b>ISO Data</b>		
Flexural modulus, 23°C	1600	MPa
Charpy notched impact strength, +23°C	3	kJ/m <sup>2</sup>
Shore D hardness	72	-
<b>Thermal properties</b>		
<b>ISO Data</b>		
Temp. of deflection under load, 0.45 MPa	85	°C
<b>Other properties</b>		
Density	905	kg/m <sup>3</sup>

#### Characteristics

##### Processing

Injection Molding

##### Additives

Release agent

##### Features

Tribologic Grade, Homopolymer

##### Chemical Resistance

General Chemical Resistance

##### Certifications

Food contact

##### Regional Availability

North America, Europe, South and Central America, Near East/Africa